

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	3070	MPa	ASTM D 638
Tensile Strength at Yield	47	MPa	ASTM D 638
Flexural Modulus	3320	MPa	ASTM D 790
Flexural Strength	84	MPa	ASTM D 790
Shore D Hardness	80	-	ASTM D 2240
Izod Impact notched, 1/8 in	64	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Coefficient of Thermal Expansion, MD	59	E-6/K	ASTM D 696

Other properties	Value	Unit	Test Standard
Density	1510	kg/m ³	ASTM D 792

Characteristics

Processing
Profile Extrusion, Other Extrusion

Delivery form
Powder

Special Characteristics
U.V. stabilized or stable to weather

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa