

Geon™ Vinyl Fittings M1150

PVC

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2760	MPa	ASTM D 638
Tensile Strength at Yield	46.1	MPa	ASTM D 638
Shore D Hardness	80	-	ASTM D 2240
Izod Impact notched, 1/8 in	1200	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1390	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	199 - 210	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Certifications

Drinking water contact, Drinking water contact NSF 61

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa