

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2300	MPa	ASTM D 638
Tensile Strength at Yield	44.8	MPa	ASTM D 638
Flexural Modulus	2650	MPa	ASTM D 790
Flexural Strength	83.4	MPa	ASTM D 790
Rockwell Hardness	R 105	-	ASTM D 785
Shore D Hardness	80	-	ASTM D 2240
Izod Impact notched, 1/8 in	1100	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	69.4	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Applications

General Purpose, Packaging

Special Characteristics

High impact or impact modified, Transparent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa