

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2450	MPa	ASTM D 638
Tensile Strength at Yield	45.4	MPa	ASTM D 638
Shore D Hardness	80	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ASTM D 792

Characteristics

Processing

Blow Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Transparent

Chemical Resistance

General Chemical Resistance

Applications

General Purpose, Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa