

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2690	MPa	ASTM D 638
Tensile Strength at Yield	42.1	MPa	ASTM D 638
Flexural Modulus	2650	MPa	ASTM D 790
Flexural Strength	80	MPa	ASTM D 790
Shore D Hardness	83	-	ASTM D 2240
Izod Impact notched, 1/8 in	1000	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	65	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ASTM D 792

Characteristics

Delivery form
Pellets

Special Characteristics
High impact or impact modified, Transparent

Features
Low Odor

Certifications
Food contact, Food approval FDA 21 CFR

Applications
Packaging

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa