

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	49.4	MPa	ASTM D 638
Elongation at Break	55	%	ASTM D 638
Shore D Hardness	77	-	ASTM D 2240
Izod Impact notched, 1/8 in	1100	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ASTM D 792

Characteristics

Processing

Blow Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Transparent

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa