

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	53.4	MPa	ASTM D 638
Flexural Modulus	2840	MPa	ASTM D 790
Flexural Strength	88.5	MPa	ASTM D 790
Shore D Hardness	82	-	ASTM D 2240
Izod Impact notched, 1/8 in	140	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ASTM D 792

Characteristics

Processing

Profile Extrusion, Other Extrusion

Delivery form

Pellets

Special Characteristics

Transparent

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa