

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2870	MPa	ASTM D 638
Tensile Strength at Yield	56.9	MPa	ASTM D 638
Flexural Modulus	2920	MPa	ASTM D 790
Flexural Strength	93.5	MPa	ASTM D 790
Shore D Hardness	85	-	ASTM D 2240
Izod Impact notched, 1/8 in	21	J/m	ASTM D 256
Thermal properties			
ASTM Data	Value	Unit	Test Standard
Coefficient of Thermal Expansion, MD	70	E-6/K	ASTM D 696
DTUL @ 264 psi	61.1	°C	ASTM D 648
Other properties			
Value	Unit	Test Standard	
Density	1380	kg/m ³	ASTM D 792

Characteristics

Processing

Profile Extrusion, Other Extrusion

Delivery form

Pellets

Special Characteristics

Transparent

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa