

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>3210</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>44.1</b>	MPa	ASTM D 638
Flexural Modulus	<b>3050</b>	MPa	ASTM D 790
Flexural Strength	<b>83.2</b>	MPa	ASTM D 790
Shore D Hardness	<b>78</b>	-	ASTM D 2240
Izod Impact notched, 1/8 in	<b>1100</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	<b>58</b>	E-6/K	ASTM D 696
DTUL @ 264 psi	<b>68.9</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1440</b>	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Profile Extrusion, Other Extrusion

#### Delivery form

Pellets

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa