

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>2590</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>44.1</b>	MPa	ASTM D 638
Flexural Modulus	<b>2620</b>	MPa	ASTM D 790
Flexural Strength	<b>78.2</b>	MPa	ASTM D 790
Shore D Hardness	<b>83</b>	-	ASTM D 2240
Izod Impact notched, 1/8 in	<b>1300</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Coefficient of Thermal Expansion, MD	<b>67</b>	E-6/K	ASTM D 696
DTUL @ 264 psi	<b>68.9</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>1350</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Profile Extrusion, Other Extrusion

**Delivery form**

Pellets

**Features**

Melt Strength

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa