

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2340	MPa	ASTM D 638
Tensile Strength at Yield	39.3	MPa	ASTM D 638
Elongation at Break	160	%	ASTM D 638
Shore D Hardness	80	-	ASTM D 2240
Izod Impact notched, 1/8 in	910	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	750	J/m	ASTM D 256
Temperature	0	°C	-

Other properties	Value	Unit	Test Standard
Density	1340	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Certifications

Recycled Resin Content

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa