

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	3030	MPa	ASTM D 638
Tensile Strength at Yield	51.7	MPa	ASTM D 638
Shore D Hardness	81	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1300	kg/m ³	ASTM D 792

Characteristics

Processing
Profile Extrusion, Other Extrusion

Special Characteristics
Transparent

Delivery form
Pellets

Regional Availability
North America