

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	2450	MPa	ASTM D 638
Tensile Strength	45.5	MPa	ASTM D 638
Elongation at Break	32	%	ASTM D 638
Flexural Modulus	2520	MPa	ASTM D 790
Flexural Strength	70.3	MPa	ASTM D 790
Shore D Hardness	81	-	ASTM D 2240
Izod Impact notched, 1/8 in	640	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	67.2	°C	ASTM D 648
DTUL @ 264 psi	57	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1350	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Delivery form

Pellets

### Regional Availability

North America