

LITAC-A™ 120PCF

SAN

Nippon A&L Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	29	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Other Standards^[S]			
Molding shrinkage, parallel	0.3	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	69	MPa	ISO 527
Flexural modulus, 23°C	3600	MPa	ISO 178
Flexural strength	121	MPa	ISO 178
Charpy notched impact strength, +23°C	1.5	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 127	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	60	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	1070	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3 - 6	h	-
Melt temperature	210 - 250	°C	-
Mold temperature	50 - 70	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific