

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.2	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	27	MPa	ISO 527
Stress at break	30	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1200	MPa	ISO 178
Shore D hardness	64	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	135	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	953	kg/m ³	ISO 1183

Characteristics

Processing

Pipe/Tube Extrusion

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Features

Melt Strength

Chemical Resistance

Oxidation Resistance

Regional Availability

Europe, Near East/Africa