

Dryflex® DW 75A001N L

SEBS

Hexpol TPE

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	20.3	MPa	ISO 37
Strain at break	859	%	ISO 37
Tear strength	54.4	kN/m	ISO 34-1

Other properties	Value	Unit	Test Standard
Density	890	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 3	h	-
Mold temperature	15 - 60	°C	-
Feed temperature	170 - 190	°C	-
Zone 1	180 - 200	°C	-
Zone 2	190 - 210	°C	-
Zone 3	200 - 210	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Natural Color

Features

Good Adhesion

Certifications

Food contact, Food approval 10/2011, Drinking water contact, Drinking water contact KTW, Drinking water contact DVGW W270

Regional Availability

North America, Europe, Asia Pacific