

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	4.3	MPa	ASTM D 638
Elongation at Break	600	%	ASTM D 638
Modulus at 100% Elongation	1.8	MPa	ASTM D 412
Modulus at 300% Elongation	3	MPa	ASTM D 412
Shore A Hardness	50	-	ASTM D 2240
Tear Strength	24	kN/m	ASTM D 624
Compression Set , 22 hr @ 158 °F	47	%	ASTM D 395

Other properties	Value	Unit	Test Standard
Density	960	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Features

Good Adhesion

Chemical Resistance

Acid Resistance, Alkali Resistance, Ozone Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa