

Product Texts

Mix Ratio
 Part A: 1
 Part B: 1

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	4 ^[1]	MPa	ASTM D 412
Shore A Hardness	67 ^[1]	-	ASTM D 2240
Tear Strength	27 ^[1]	kN/m	ASTM D 624
Tensile Strength	9.6 ^[1]	MPa	ASTM D 412

1: Cure condition: 10 minutes at 120°C

Other properties	Value	Unit	Test Standard
Density	1120 ^[2]	kg/m ³	ASTM D 792

2: Cure condition: 10 minutes at 120°C

Characteristics

Certifications

Food contact, Food approval BfR, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa