

Product Texts

Mix Ratio
 Part A: 1
 Part B: 1

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|---------------------|-------------|----------------------|
| ASTM Data | | | |
| Modulus at 100% Elongation | 1.65 ^[1] | MPa | ASTM D 412 |
| Shore A Hardness | 50 ^[1] | - | ASTM D 2240 |
| Tear Strength | 41 ^[1] | kN/m | ASTM D 624 |
| Tensile Strength | 9.5 ^[1] | MPa | ASTM D 412 |

1: Cure condition: 10 minutes at 120°C

| Other properties | Value | Unit | Test Standard |
|-------------------------|---------------------|-------------------|----------------------|
| Density | 1110 ^[2] | kg/m ³ | ASTM D 792 |

2: Cure condition: 10 minutes at 120°C

Characteristics

Certifications

Food contact, Food approval BfR, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa