

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>60</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>43</b>	MPa	ASTM D 638
Elongation at Yield	<b>7.3</b>	%	ASTM D 638
Elongation at Break	<b>180</b>	%	ASTM D 638
Flexural Modulus	<b>2058</b>	MPa	ASTM D 790
Flexural Strength	<b>94</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 119</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>50</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>3.2</b>	mm	-
DTUL @ 66 psi	<b>112</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>105</b>	°C	ASTM D 648

Optical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Haze	<b>1</b>	%	ASTM D 1003
Light Transmittance	<b>87</b>	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	<b>1270</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Sheet Extrusion

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat, Transparent

**Features**

Good Adhesion, Copolymer

**Chemical Resistance**

General Chemical Resistance, Stain Resistance

**Certifications**

Contains renewable resources, Food contact

**Applications**

General Purpose, Packaging

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America