

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0025</b>	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>47</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>48</b>	MPa	ASTM D 638
Elongation at Yield	<b>5.8</b>	%	ASTM D 638
Elongation at Break	<b>150</b>	%	ASTM D 638
Flexural Modulus	<b>1860</b>	MPa	ASTM D 790
Flexural Strength	<b>71</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 115</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>N</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>3.2</b>	mm	-
DTUL @ 66 psi	<b>80</b>	°C	ASTM D 648

Optical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Haze	<b>1</b>	%	ASTM D 1003
Light Transmittance	<b>89</b>	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	<b>1250</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Special Characteristics**  
 Flame retardant, High impact or impact modified, Heat stabilized or stable to heat, Transparent

**Features**  
 Copolymer

**Chemical Resistance**  
 General Chemical Resistance, Stain Resistance

**Certifications**  
 Contains renewable resources

**Applications**  
 Electrical and Electronical, Refrigeration

**Regional Availability**  
 North America, Europe, Asia Pacific, South and Central America