

Product Texts

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® G4774 is a medium modulus grade with nominal hardness of 47D. It contains discoloring stabilizer. It can be processed by many conventional thermoplastic processing techniques like injection molding and extrusion.

Typical applications:

Hose and tubing, wire and cable jackets, film and sheeting, profiles and moulded products. Not suited for light-colored finished products.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	11	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	1.5	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
^[C] Density of melt	1010	kg/m ³	-
^[C] Thermal conductivity of melt	0.16	W/(m K)	-
^[C] Spec. heat capacity of melt	2100	J/(kg K)	-
^[C] Eff. thermal diffusivity	5.44E-8	m ² /s	-
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.014	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	N	kJ/m ²	ISO 179/1eA
^[C] Tensile notched impact strength, +23°C	260	kJ/m ²	ISO 8256/1
^[C] Stress at 10% elongation	7	MPa	ISO 527
^[C] Stress at break TPE	17	MPa	ISO 527
^[C] Strain at break TPE	200	%	ISO 527
^[C] Abrasion resistance	33	mm ³	ISO 4649
^[C] Shore D hardness	43	-	ISO 7619-1
ASTM Data			
Tensile Strength at Break	20.7	MPa	ASTM D 638
Elongation at Break	275	%	ASTM D 638
Flexural Modulus	117	MPa	ASTM D 790
Shore D Hardness	47	-	ASTM D 2240
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	144	J/m	ASTM D 256
Temperature	-40	°C	-

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	208	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	-45	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	60	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	220	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	190	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
^[C] Burning rate, FMVSS, Thickness 1 mm	33	mm/min	ISO 3795 (FMVSS 302)
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
Coefficient of Thermal Expansion, MD	220	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	210	E-6/K	ASTM D 696
DTUL @ 66 psi	72	°C	ASTM D 648
DTUL @ 264 psi	45	°C	ASTM D 648
Melting Temperature	208	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 1MHz	4.7	-	IEC 62631-2-1
^[C] Volume resistivity	1E12	Ohm*m	IEC 62631-3-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1190	kg/m ³	ISO 1183
Water Absorption, 24hr	2.5	%	ASTM D 570
Density	1200	kg/m ³	ASTM D 792

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Film Extrusion, Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Wire/Cable Extrusion, Other Extrusion, Coating, Blow Molding, Casting, Thermoforming

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Platable, Heat stabilized or stable to heat

Features

Color Stability, Copolymer

Chemical Resistance

Oxidation Resistance

Applications

General Purpose, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa