

Product Texts

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® HTR8068 is a medium modulus flame retardant and antidrip Hytrel® resin that meets the requirement of UL94 V-0. It has nominal durometer hardness of 44D.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	3.6	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
^[C] Density of melt	1300	kg/m ³	-
^[C] Eff. thermal diffusivity	5.44E-8	m ² /s	-
ASTM Data			
Melt Flow Index, MFI	4.6	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	40	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	7	kJ/m ²	ISO 179/1eA
^[C] Stress at 10% elongation	5.9	MPa	ISO 527
^[C] Stress at break TPE	13	MPa	ISO 527
^[C] Strain at break TPE	>300	%	ISO 527
^[C] Shore D hardness	38	-	ISO 7619-1
ASTM Data			
Tensile Strength at Break	12.4	MPa	ASTM D 638
Elongation at Break	340	%	ASTM D 638
Flexural Modulus	174	MPa	ASTM D 790
Shore D Hardness	46	-	ASTM D 2240
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	90	J/m	ASTM D 256
Temperature	-40	°C	-

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	170	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	41	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	46	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	150	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	170	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10

Hytrell® HTR8068

TPC

Celanese

Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
^[C] Oxygen index	26	%	ISO 4589-1/-2
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
Melting Temperature	169	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	6.8	-	IEC 62631-2-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1430	kg/m ³	ISO 1183
Water Absorption, 24hr	1.9	%	ASTM D 570
Density	1430	kg/m ³	ASTM D 792

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Film Extrusion, Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Wire/Cable Extrusion, Other Extrusion, Coating, Casting, Thermoforming

Delivery form

Pellets

Special Characteristics

Flame retardant, Platable, Light stabilized or stable to light, Heat stabilized or stable to heat

Chemical Resistance

Oxidation Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa