

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	77	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	N	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	47	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	206	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1180	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Other Extrusion, Blow Molding

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa