

RTP 1500-40D UV NATURAL

TPC

RTP Company

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	68.95	MPa	ASTM D 638
Tensile Strength	3.45	MPa	ASTM D 638
Flexural Modulus	68.95	MPa	ASTM D 790
Flexural Strength	2.61	MPa	ASTM D 790
Shore D Hardness	40	-	ASTM D 2240
Izod Impact notched, 1/8 in	85.4	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1150	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	93.3	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	210 - 238	°C	-
Mold temperature	21.1 - 48.9	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Natural Color

Regional Availability

North America, Europe, Asia Pacific