

ADPOLY MB-100

TPE

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	27.5	MPa	ASTM D 790
Flexural Strength	1.5	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	54	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	890	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

High impact or impact modified

Regional Availability

North America, Europe, Asia Pacific

Features

Good Adhesion