

APINAT™ DP2228

TPE

Grade is obsolete.

Trinseo

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	52	MPa	ASTM D 638
Elongation at Break	20	%	ASTM D 638
Flexural Modulus	2170	MPa	ASTM D 790
Shore D Hardness	78	-	ASTM D 2240
Tear Strength	149	kN/m	ASTM D 624
Other properties			
Density	1240	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Pellets

CertificationsContains renewable resources, Biodegradable, Compostable
ISO 13432 (Producer), Compostable ASTM D6400 (Producer)**Regional Availability**North America, Europe, Asia Pacific, South and Central America,
Near East/Africa