

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.023	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	42	-	ASTM D 2240
Tensile Strength at Break	3.47	MPa	ASTM D 412
Elongation at Break	580	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	918	kg/m ³	ASTM D 792

Characteristics

Features

Good Adhesion

Regional Availability

North America

Applications

Medical