

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at 100% elongation	1.6	MPa	ISO 527
Stress at 300% elongation	2.1	MPa	ISO 527
Tensile Strength	4.4	MPa	ISO 37
Strain at break	650	%	ISO 37
Compression set at 70 °C, 24h	42	%	ISO 815
Tear strength	19	kN/m	ISO 34-1
Shore A hardness	60	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183
Biobased content	25	%	-

Characteristics

Features

Good Adhesion, Soft Feel

Certifications

Contains renewable resources

Applications

Automotive, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific