

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	7.446	MPa	ASTM D 638
Tensile Strength	1.81	MPa	ASTM D 638
Elongation at Break	110	%	ASTM D 638
Flexural Modulus	4.9	MPa	ASTM D 790
Shore D Hardness	60	-	ASTM D 2240
Tear Strength	15.1	kN/m	ASTM D 624

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	192	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	440	kg/m ³	ASTM D 792

Characteristics

Processing

Additive Manufacturing

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Powder, White