

DuraGrip® DGR 6070BK

TPE

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	8.94	MPa	ISO 527
Strain at break	>50	%	ISO 527
ASTM Data			
Modulus at 100% Elongation	2.62	MPa	ASTM D 412
Modulus at 300% Elongation	3.43	MPa	ASTM D 412
Shore A Hardness	72	-	ASTM D 2240
Tear Strength	28.5	kN/m	ASTM D 624
Other properties			
Density	985	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Black

Features

High Coefficient of Friction

Applications

General Purpose

Regional Availability

North America, Europe