

**DuraGrip® DGR 6150BK**

TPE

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.021	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	5.9	MPa	ISO 527
Strain at break	>50	%	ISO 527
<b>ASTM Data</b>			
Modulus at 100% Elongation	1.79	MPa	ASTM D 412
Shore A Hardness	52	-	ASTM D 2240
Tear Strength	25.6	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	19	%	ASTM D 395
Compression Set , 22 hr @ 158 °F	76	%	ASTM D 395

Other properties	Value	Unit	Test Standard
Density	1060	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Regional Availability**

North America, Europe

**Features**

Soft Feel