

DuraGrip® DGR 6170NC

TPE

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Strain at break	>50	%	ISO 527
ASTM Data			
Modulus at 100% Elongation	2.39	MPa	ASTM D 412
Shore A Hardness	69	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1110	kg/m ³	ISO 1183
Density	1110	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Features

Soft Feel

Delivery form

Natural Color

Regional Availability

North America, Europe