

**Elastocon® 2860L**

TPE

Elastocon TPE Technologies

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>5.86</b>	MPa	ASTM D 638
Modulus at 100% Elongation	<b>2</b>	MPa	ASTM D 412
Shore A Hardness	<b>60</b>	-	ASTM D 2240
Compression Set , 22 hr @ 158 °F	<b>17</b>	%	ASTM D 395

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>880</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding, Other Extrusion, Blow Molding

**Delivery form**

Pellets

**Special Characteristics**

U.V. stabilized or stable to weather

**Features**

Tribologic Grade

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Medical

**Regional Availability**

North America