

Product Texts

Strippable semiconductive, vulkanizable compound.
Property values: Cure times were 15 minutes at 175°C.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	11.7	MPa	ASTM D 638
Elongation at Break	320	%	ASTM D 638

Electrical properties	Value	Unit	Test Standard
Other Standards^[5]			
Volume Resistivity	25	Ohm*cm	ASTM D 991

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1160	kg/m ³	ASTM D 792

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	115 - 125	°C	-

Characteristics

Processing

Wire/Cable Extrusion

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa