

Evoprene® G 3462

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	5	MPa	ISO 37
Strain at break	615	%	ISO 37
Compression set at 70 °C, 24h	39	%	ISO 815
Shore A hardness	48	-	ISO 7619-1
Other Standards^[5]			
Stress at 100% elongation	1.25	MPa	ISO 37
Stress at 300% elongation	6.6	MPa	ISO 37

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Other Standards^[5]			
Density	1030	kg/m ³	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe