

Evoprene® G 6260 Black 5156

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	6.6	MPa	ISO 37
Strain at break	578	%	ISO 37
Compression set at 70 °C, 24h	31	%	ISO 815

Other properties	Value	Unit	Test Standard
Other Standards^[S]			
Density	970	kg/m ³	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Processing

Injection Molding

Features

Copolymer

Delivery form

Black

Regional Availability

North America, Europe