

**Faraprene R100-95A BK**

TPE

Primex Color, Compounding &amp; Additives

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>11.7</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Modulus at 100% Elongation	<b>5.55</b>	MPa	ASTM D 412
Shore A Hardness	<b>97</b>	-	ASTM D 2240
Tear Strength	<b>41.1</b>	kN/m	ASTM D 624
Tensile Strength at Break	<b>7.72</b>	MPa	ASTM D 412
Elongation at Break	<b>368</b>	%	ASTM D 412
<b>Other properties</b>			
Density	<b>1150</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Black

**Certifications**

Recycled Resin Content

**Applications**

Automotive, IT / Business Machine, Electrical and Electronical

**Regional Availability**

North America