

GFE 4771-A8 NAT OR-1

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	80	-	ASTM D 2240
Tensile Strength	13.1	MPa	ASTM D 412
Elongation at Break	360	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	34	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1440	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Regional Availability

North America, Europe

Special Characteristics

Flame retardant