

GFE 4777-A6 NATURAL LCF

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	87	-	ASTM D 2240
Tensile Strength	17.2	MPa	ASTM D 412
Elongation at Break	350	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	25	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1250	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Regional Availability

North America, Europe

Special Characteristics

Flame retardant, U.V. stabilized or stable to weather