

GFEX 05-384-G NATURAL LCF

TPE

Alphagary

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Shore A Hardness | 80 | - | ASTM D 2240 |
| Tensile Strength | 8.27 | MPa | ASTM D 412 |
| Elongation at Break | 300 | % | ASTM D 412 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1410 | kg/m ³ | ASTM D 792 |

Characteristics**Delivery form**

Natural Color

Regional Availability

North America, Europe

Applications

Electrical and Electronical