

GFG 7788-A6 NAT

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	95	-	ASTM D 2240
Tensile Strength	12.1	MPa	ASTM D 412
Elongation at Break	550	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	25	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Special Characteristics

Flame retardant

Chemical Resistance

Oil Resistance

Applications

Electrical and Electronical

Regional Availability

North America, Europe