

**JSR EXCELINK® 3400B**

TPE

JSR Corporation

| <b>Processing/Physical Characteristics</b> | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|--|--------------|-------------|----------------------|
| <b>ISO Data</b>                            |              |             |                      |
| Melt flow index, MFI                       | <b>3</b>     | g/10min     | ISO 1133             |
| Temperature                                | <b>230</b>   | °C          | -                    |
| Load                                       | <b>2.16</b>  | kg          | -                    |

| <b>Mechanical properties</b> | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|------------------------------|--------------|-------------|----------------------|
| <b>ISO Data</b>              |              |             |                      |
| Tensile Strength             | <b>4.5</b>   | MPa         | ISO 37               |
| Strain at break              | <b>1000</b>  | %           | ISO 37               |
| Shore A hardness             | <b>33</b>    | -           | ISO 7619-1           |

| <b>Other properties</b> | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|-------------------------|--------------|-------------------|----------------------|
| Density                 | <b>880</b>   | kg/m <sup>3</sup> | ISO 1183             |

**Characteristics****Features**

Crosslinkable, High Crystallinity

**Regional Availability**

North America, Europe, Asia Pacific

**Applications**

Packaging