

KIBITON PB-5301

TPE

CHIMEI Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.5	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	75	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Asia Pacific