

KIBITON PB-5502

TPE

CHIMEI Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	79	-	ASTM D 2240
Tensile Strength at Break	3.4	MPa	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Asia Pacific