

KOPEL® KP3335

TPE

Kolon Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	26	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	16	MPa	ASTM D 638
Flexural Modulus	28	MPa	ASTM D 790
Shore D Hardness	37	-	ASTM D 2240
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	N	J/m	ASTM D 256
Temperature	-40	°C	-
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Melting Temperature	160	°C	ASTM D 3418
Other properties			
Density	1130	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Asia Pacific