

KOPEL® KP3340RA

TPE

Kolon Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	23	MPa	ASTM D 638
Shore D Hardness	39	-	ASTM D 2240
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Izod Impact notched, Low-Temperature Temperature	N -40	J/m °C	ASTM D 256 -

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Melting Temperature	144	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1120	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

North America, Asia Pacific