

**KOPEL® KP3346MP**

TPE

Kolon Industries

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>9</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Shore D Hardness	<b>45</b>	-	ASTM D 2240
Taber Abrasion Resistance	<b>40</b>	mg/1000 cycles	ASTM D 1044
Izod Impact notched, 1/8 in	<b>N</b>	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	<b>N</b>	J/m	ASTM D 256
Temperature	<b>-40</b>	°C	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
<b>Other properties</b>			
Density	<b>1140</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Regional Availability**

North America, Asia Pacific