

Product Texts

Available in light-grey color.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	13	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Strength	9	MPa	ISO 527
Strain at break	870	%	ISO 527
Shore A hardness	76	-	ISO 7619-1

Other properties

	Value	Unit	Test Standard
Density	1160	kg/m ³	ISO 1183

Processing Recommendation Injection Molding

	Value	Unit	Test Standard
Melt temperature	220	°C	-
Mold temperature	30	°C	-

Characteristics**Processing**

Injection Molding

Chemical Resistance

Solvent Resistance, Ozone Resistance

Special Characteristics

Light stabilized or stable to light, Heat stabilized or stable to heat

Regional Availability

Europe

Features

Copolymer