

Product Texts

Available in natural and black colors.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Strength	7	MPa	ISO 527
Strain at break	655	%	ISO 527
Shore A hardness	80	-	ISO 7619-1

Other properties

	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Processing Recommendation Injection Molding

	Value	Unit	Test Standard
Melt temperature	180	°C	-
Mold temperature	30	°C	-

Characteristics**Processing**

Injection Molding, Wire/Cable Extrusion

Special Characteristics

Light stabilized or stable to light

Features

Thermal Stability

Chemical Resistance

General Chemical Resistance, Solvent Resistance, Ozone Resistance

Applications

Electrical and Electronical

Regional Availability

Europe